

Summary of Technical Data Sheet

Product designation:	Product composition / construction
WARMCEL	Cellulose Fibre Insulation

Property	Measured Values	Standard
Thermal Conductivity Lambda 90/90 23°C/50%RH	0.038 W/mK	EN 12667 EN ISO 10456 EAD 040138-00-1201
Reaction to Fire	Class E	EN 13501-1 + A1
Resistance to Mould Growth	Class E	Annex F of EN 15101-1
Specific Airflow Resistance a) bulk density 45.0 kg/m ³ b) bulk density 60.0 kg/m ³	≤13 kPa*s/m ² ≤18 kPa*s/m ²	EN29053
Critical Moisture Content	75%	EN 1609 method A
Settlement in walls & between rafters	See table on next page	Annex B.2 of EN 15101-1
Settlement by shock	≤9% (@ 30kg/m ³)	Annex B.3 of EN 15101-1
Settlement by humidity a) bulk density 30.0 kg/m ³ b) bulk density 50.0 kg/m ³	>25%; SH 30 >10%; SH 10	Annex B.1 of EN 15101-1
Density		See table on next page
Specific heat capacity	2020 ± 6% J/kg.K	EN ISO 8990, EN 675



CIUR (UK) Ltd
Aberdare Enterprise Center,
Aberman, Aberdare,
CF44 6DA
United Kingdom
T: +44 (0) 1685 878 649
F: +44 (0) 1685 875 403



PYC Insulation Ltd
The House Building Factory,
Buttington Cross Enterprise Park,
Welshpool, Powys,
SY21 8SL
United Kingdom
T: +44 (0) 1938 500 797
E: info@pycgroup.co.uk



CIUR Ltd reserves the right to amend product specifications without prior notice. The information given in this document is given with good faith and any recommendations for use should be verified as to suitability and compliance with actual requirements, specifications and applicable laws and regulations.
November 21, 2016 Based on information valid at the time of publishing.
The manufacturer reserves the right to change the given data.

Summary of Technical Data Sheet

Prescribed installed densities for Warmcel

The figures show are the minimum densities required in order to prevent settlement

Open blown lofts

Thickness of insulation (mm)	100-180	190-240	250-300	310-350	360-500	510-600
Minimum density (kg/m ³)	30	33	36	38	41	45

Flat ceilings and Floors

Thickness of insulation (mm)	100-120	130-170	180-240	250-300	310-350	360-500
Minimum density (kg/m ³)	34	37	40	44	47	52

Sloping ceilings up to 30 °

Thickness of insulation (mm)	100-130	140-170	180-200	210-300	310-350	360-500
Minimum density (kg/m ³)	40	44	47	49	52	55

Sloping ceilings 30 ° - 45 °

Thickness of insulation (mm)	100-130	140-170	180-200	210-300	310-350	360-500
Minimum density (kg/m ³)	45	48	48	50	53	56

Sloping ceilings 45 ° - 90 °

Thickness of insulation (mm)	100-130	140-170	180-200	210-300	310-350	360-500
Minimum density (kg/m ³)	50	53	56	58	60	63

Walls

Thickness of insulation (mm)	100-130	140-170	180-200	210-300	310-350	360-500
Minimum density (kg/m ³)	50	53	56	58	60	63

For factory filled timber frame panels (where the panels are subjected to transport and excess movement) the minimum fill density for all applications is 60kg/m³ (65kg/m³ for installed thicknesses of 200mm and above).

Notes:

1. Values are Means (not minimum) obtained from initial type testing.
2. Values stated are in the weaker principle direction.



CIUR (UK) Ltd
Aberdare Enterprise Center,
Aberman, Aberdare,
CF44 6DA
United Kingdom
T: +44 (0) 1685 878 649
F: +44 (0) 1685 875 403



PYC Insulation Ltd
The House Building Factory,
Buttington Cross Enterprise Park,
Welshpool, Powys,
SY21 8SL
United Kingdom
T: +44 (0) 1938 500 797
E: info@pycgroup.co.uk



CIUR Ltd reserves the right to amend product specifications without prior notice. The information given in this document is given with good faith and any recommendations for use should be verified as to suitability and compliance with actual requirements, specifications and applicable laws and regulations.
November 21, 2016 Based on information valid at the time of publishing.
The manufacturer reserves the right to change the given data.